

## RAK Enamel Gloss

---

### Product description

This is a one component oxidatively drying superior quality coating based on alkyd resin. Can be used interior & exterior surfaces. Product offers brilliant high gloss finish & gloss retention, low yellowing, abrasion resistance, smooth and durable finish.

### Typical use

For interior and exterior concrete surfaces, cement plaster, block work, primed timber and metal surfaces.

### Finish

As per RAK Shade Card

---

### Product data

Property	Description
Gloss level (GU 60 °)	80 – 95 (Glossy)
Solids by Volume	39 ± 2 %
Flash point	36°C
Density	1.06 kg/l
VOC-EU	374 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

All data is valid for mixed paint.

Gloss description: According to RAK Performance Coatings' definition.

---

### Film thickness per coat

#### Typical recommended specification range

Dry film thickness	30	-	40	µm
Wet film thickness	77	-	103	µm
Theoretical spreading rate	13	-	9.75	m <sup>2</sup> /l

### Surface preparation

Surface should be clean from all dust, rust, wax, oil, grease, loose particles, flakes and other contaminants. Remove all wax, oil and grease by solvent cleaning as per instruction given by SSPC-SP1. Light sanding with abrasive material is recommended, resulting dust should be removed properly. Surface to be recoat should clean thoroughly before application.

## RAK Enamel Gloss

---

### Application

#### Application methods

The product can be applied by

Roller : Recommended

Spray : Use Air or Airless Spray

Brush : Use for corners and areas difficult to paint with roller

---

#### Product mixing

Single Pack.

---

#### Thinner/Cleaning solvent

Thinner: RAK Enamel Thinner

5-10% thinner is recommended as per need.

---

#### Guiding data for Airless spray

Nozzle tip Size : 0.15 – 0.025 inch

Pressure at nozzle (minimum): 2000 psi

Apply this product only if relative humidity is less than 85% and substrate temperature is minimum 10° C & above 3° C of the dew point

---

### Drying and Curing time

Surface Dry	120 Minutes
Tack free	10 Hours
Full Cure	Overnight
Recoating Time (Minimum)	12 Hours

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, 30° C temperature and at average of the DFT range for the product.

---

#### Pot Life

Single Pack

---

## RAK Enamel Gloss

---

### Product Application System

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact RAK Paint for specific system recommendation.

**A) For Concrete Surface**

Previous coat : RAK PVA or Acrylic Primer – 1 Coat + 2 coats of RAK Superfine Putty

Topcoat : RAK Enamel Gloss – 2 Coats

**B) For Wooden Surface**

Previous coat : RAK Synthetic Primer / Wood Primer – 1 Coat

Topcoat : RAK Enamel Gloss – 2 Coat

**C) For Metal Surface**

Previous coat : RAK Primer Redoxide / RAK Zinc Phosphate Primer / RAK Grey Oxide Primer – 1 Coat

Topcoat : RAK Enamel Gloss – 2 Coat

---

### Packaging (typical)

RAK Enamel Gloss                      0.9L, 3.6L & 18L

---

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

---

### Shelf life at 30 °C

RAK Enamel Gloss                      24 Months

---

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

---

### Health and safety

During paint application, it is advisable to wear suitable protective guards (PPE). In case of accidental contact with eyes rinse immediately with plenty of water and seek medical advice. In case of inhalation- remove to fresh air, loosen collar and keep patient rested. Get medical treatment. For remove splashes from skin, use soap and water or approved skin cleanser. Flammable material always keeps away from sources of ignition and do not smoke. Ensure sufficient ventilation during application and drying. Do not breathe vapour/spray. Keep container tightly closed and keep out of reach of children. In case of fire - use foam, carbon dioxide or dry chemicals. For more information, refer MSDS.

---

### Disclaimer

The data provided in this sheet is given to the best of our knowledge and based on laboratory testing and practical experience. We cannot guarantee anything but the product since the conditions and methods during application vary. We reserve the right to change the given data without prior notice. The product data sheet supersedes those previously issued.

For more information, contact your local RAK Paints Representative, go to [www.rakpaints.com](http://www.rakpaints.com) or call +971-7-2444036.

RAK Paints LLC, PO Box: 86012, Tel: +971-7-2444036, Fax: +971-7-2446110, Ras Al Khaimah, UAE. [www.rakpaints.com](http://www.rakpaints.com)

---