

RAK Gypseal 2080

Product description

RAK GYPSEAL 2080 is a ready -to-use gypsum jointing compound and Multi-purpose joint filler, made of high quality binders and selected non-toxic fillers. It is suitable for a wide range of interior and weather protected exterior for non-structural filling; achieve smooth and seamless walls and ceilings. The ready -to-use Gypseal 2080 is easy to apply making it ideal for simple home renovations and do it yourself fixes. It can be used over concrete, plywood, wood, gypsum or fibre cement boards embedding fasteners, reinforcing tape& plastic or metal trim filling knots, dents, splits, nail holes & correcting other minor surface imperfections prior to finishing. Gypseal 2080 is an Eco-friendly product, which have low volatile organic compound(VOC) levels bearing little or no adverse effects to the environment.

Typical use

For use on interior surfaces i.e. cement plaster, concrete, masonry, brick work, asbestos, rendered block work, gypsum board etc.

Colours

White

Product data

Property	Description
Gloss level (GU 60 °)	Matt
Solids by volume	55 ± 2 % Only for White Colour
Density	1.83 kg/l
VOC-ISO 11890 EU	7 g/l*

* This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

The provided data is typical for factory produced products, subject to slight variation depending on colour. All data is valid for mixed paint.

Gloss description: According to RAK Decorative Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	85	-	130	µm
Wet film thickness	155	-	237	µm
Theoretical spreading rate	6.5	-	4.2	m ² /l

The Actual Spreading Rate will depend on the actual dry film thickness, the nature of substrate, imperfections, temperature, the application method and the losses in container and application. Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

RAK Paints LLC, PO Box: 86012, Tel: +971-7-2444036, Fax: +971-7-2446110, Ras Al Khaimah, UAE. www.rakpaints.com

RAK Gypseal 2080

Surface preparation

The surface must be cleaned of any dust, oil, grease, poorly adhering materials, etc. It should be clean, dry and well primed. All loose materials must be thoroughly rubbed down using a suitable abrasive paper. Any resulting dust/loose particles must be removed. All traces of form release agents/curing agents must be removed.

Application

Application methods

Putty Knife : This product is recommended to be applied only by Putty Knife

Use several light strokes to cover regular application area. If necessary, put a mesh tape on top of the crack or joint before applying the mixture. Build up a smooth, finish surface, allowing each coat to dry completely. Sand the final coat prior to finishing i.e,24 Hours prior to applying final coat.

Apply this product only if relative humidity is less than 85% and substrate temperature is minimum 10° C & above 3° C of the dew point

Thinner / Cleaning of Painting Tools

Water

Dilution

Do not add water to dilute the consistency of premixed putty. This could lead to cracking & excessive shrinkage.

Drying and Curing time

Surface Dry	60 Minutes
Hard Dry	6 Hours
Recoating Time (Minimum)	6 Hours

Drying and curing times are determined under controlled temperatures and relative humidity below 50 %, temperature 30° C and at average of the DFT range for the product.

RAK Gypseal 2080

Packaging (typical)

RAK Gypseal 2080

5 kg and 25 kg

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 30 °C

RAK Gypseal 2080

12 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Health and safety

During paint application, it is advisable to wear suitable protective guards (PPE). In case of accidental contact with eyes rinse immediately with plenty of water and seek medical advice. In case of inhalation- remove to fresh air, loosen collar and keep patient rested. Get medical treatment. For remove splashes from skin, use soap and water or approved skin cleanser. Flammable material always keeps away from sources of ignition and do not smoke. Ensure sufficient ventilation during application and drying. Do not breathe vapour/spray. Keep container tightly closed and keep out of reach of children. In case of fire - use foam, carbon dioxide or dry chemicals. For more information, refer MSDS.

Disclaimer

The data provided in this sheet is given to the best of our knowledge and based on laboratory testing and practical experience. We cannot guarantee anything but the product since the conditions and methods during application vary. We reserve the right to change the given data without prior notice. The product data sheet supersedes those previously issued.

For more information, contact your local RAK Paints Representative, go to www.rakpaints.com or call +971-7-2444036.