Technical Data Sheet



RAK PVA Primer

Product description

A primer based on PVA co-polymer having excellent adhesion and sealing properties for interior surfaces. It gives a smooth surface for the application of subsequent top coat. It also has good in can antifungal and antibacterial properties.

Typical use

For use on interior surfaces i.e. cement plaster, concrete, masonry, brick work, asbestos, rendered block work, etc.

Colours

White

Product data

Property	Description		
Gloss level (GU 60 °)	Matt		
Solids by volume	34 ± 2 %		
Density	1.5 kg/l		
VOC-ISO 11890 EU	9 g/l*		

^{*} This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

The provided data is typical for factory produced products, subject to slight variation depending on colour. All data is valid for mixed paint.

Gloss description: According to RAK Decorative Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	20	- 25	μm
Wet film thickness	60	- 75	μm
Theoretical spreading rate	17	- 11	m²/l

The Actual Spreading Rate will depend on the actual dry film thickness, the nature of substrate, imperfections, temperature, the application method and the losses in container and application.

Product Code: 11003, Rev 1

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

RAK Paints LLC, PO Box: 86012, Tel: +971-7-2444036, Fax: +971-7-2446110, Ras Al Khaimah, UAE. www.rakpaints.com

Page 1 of 3

This Technical Data Sheet supersedes those previously issued.

Date of issue: 01 November 2019

Technical Data Sheet



RAK PVA Primer

Surface preparation

The surface must be cleaned of any dust, oil, grease, poorly adhering materials, etc. It should be clean, dry and well primed. All loose materials must be thoroughly rubbed down using a suitable abrasive paper. Any resulting dust/loose particles must be removed. All traces of form release agents/curing agents must be removed.

Application

Application methods

Roller: This product is recommended to be applied by using roller

Brush: Recommended for corners, edges and small areas

Spray: Use conventional spray or airless spray

Guiding data for airless spray

Nozzle Tip : 0.018" - 0.021"

Pressure at nozzle (minimum): 2000 - 2500 psi

Spray Angle : 65° -- 80°

Apply this product only if relative humidity is less than 85% and substrate temperature is minimum 10° C & above 3° C of the dew point

Thinner / Cleaning of Painting Tools

Water

Dilution

10 - 15% Recommended

Drying and Curing time

Surface Dry 60 Minutes
Hard Dry 2 - 4 Hours
Recoating Time (Minimum) 3 Hours

Drying and curing times are determined under controlled temperatures and relative humidity below 50 %, temperature 30° C and at average of the DFT range for the product.

Product Code: 11003, Rev 1

RAK Paints LLC, PO Box: 86012, Tel: +971-7-2444036, Fax: +971-7-2446110, Ras Al Khaimah, UAE. www.rakpaints.com

Page 2 of 3

Date of issue: 01 November 2019

Technical Data Sheet



RAK PVA Primer

Typical paint system

Primer : RAK PVA Primer - 1 Coat

Smoothening Coat: RAK Super Fine Putty - 2 Coats

Topcoat : RAK Topcoat - 2 or 3 coats depend up on colour

Packaging (typical)

RAK PVA Primer 3.6 L and 18 L

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 30 °C

RAK PVA Primer 24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Health and safety

During paint application, it is advisable to wear suitable protective guards (PPE). In case of accidental contact with eyes rinse immediately with plenty of water and seek medical advice. In case of inhalation- remove to fresh air, loosen collar and keep patient rested. Get medical treatment. For remove splashes from skin, use soap and water or approved skin cleanser. Flammable material always keeps away from sources of ignition and do not smoke. Ensure sufficient ventilation during application and drying. Do not breathe vapour/spray. Keep container tightly closed and keep out of reach of children. In case of fire - use foam, carbon dioxide or dry chemicals. For more information, refer MSDS.

Disclaimer

The data provided in this sheet is given to the best of our knowledge and based on laboratory testing and practical experience. We cannot guarantee anything but the product since the conditions and methods during application vary. We reserve the right to change the given data without prior notice. The product data sheet supersedes those previously issued

For more information, contact your local RAK Paints Representative, go to www.rakpaints.com or call +971-7-2444036.

Product Code: 11003, Rev 1

RAK Paints LLC, PO Box: 86012, Tel: +971-7-2444036, Fax: +971-7-2446110, Ras Al Khaimah, UAE. www.rakpaints.com

Page 3 of 3

Date of issue: 01 November 2019